## PATENT ABSTRACTS OF JAPAN

(11)Publication number:

2001-095094

(43) Date of publication of application: 06.04.2001

(51)Int.CI.

H04R 17/00

H01L 41/09

(21)Application number: 2000-

(71)Applicant: MURATA MFG CO LTD

207729

(22)Date of filing:

10.07.2000 (72)Inventor: TAKESHIMA TETSUO

KISHIMOTO KENJI

YAMAMOTO TAKASHI

HAMADA KAZURO

(30)Priority

Priority number: 11207198 Priority date: 22.07.1999 Priority country: JP

(54) PIEZOELECTRIC ELECTROACOUSTIC TRANSDUCER

BEST AVAILABLE COPY

### (57)Abstract:

PROBLEM TO BE SOLVED: To obtain a piezoelectric electroacoustic transducer, capable of constituting a bimorph-type diaphragm by simple connecting structure by eliminating the mutual connection of a main surface electrode and internal electrode. SOLUTION: Two or three piezoelectric ceramics layers 31 and 32 are laminated to form a laminated product, main surface electrodes 33 and 34 are formed on the front/rear surface of this laminated product, and an internal electrode 35 is formed

X

between each of the layers 31 and 32. All the ceramics layers 31 and 32 are polarized in the same direction in the direction of thickness, and an alternating signal is impressed between the electrodes 33, 34 and the electrode 35 to allow the laminated product to generate bending oscillation as a whole.

### **LEGAL STATUS**

[Date of request for examination]

18.04.2002

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3714128

[Date of registration]

02.09.2005

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

### \* NOTICES \*

JPO and NCIPI are not responsible for any damages caused by the use of this translation.

- 1. This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.\*\*\*\* shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

#### **CLAIMS**

[Claim(s)]

[Claim 1] Carry out the laminating of two-layer or the three-layer electrostrictive ceramics layer, and a layered product is formed. A principal plane electrode is formed in the front flesh-side principal plane of this layered product, and an internal electrode is formed between each ceramic layer. It is the piezo-electric mold electroacoustic transducer which polarization of all the ceramic layers is carried out in the same direction in the thickness direction, and is impressing an alternation signal between the above-mentioned principal plane electrode and an internal electrode, and is characterized by the above-mentioned layered product producing crookedness vibration as a whole.

[Claim 2] The above-mentioned internal electrode is a piezo-electric mold electroacoustic transducer according to claim 1 characterized by connecting with

the end-face electrode formed in the end face of a layered product, and impressing an alternation signal between the above-mentioned end-face electrode and two principal plane electrodes.

[Claim 3] It is the piezo-electric mold electroacoustic transducer according to claim 1 or 2 which the above-mentioned layered product consists of three-layer ceramic layers, and is characterized by the thickness of a middle ceramic layer being 50% - 80% of the thickness of the whole layered product.

[Claim 4] The above-mentioned layered product is a piezo-electric mold electroacoustic transducer according to claim 1 to 3 which carries out the laminating of the ceramic green sheet of two-layer or three layers through an electrode layer, is impressing an electrical potential difference to the principal plane inter-electrode which consisted of a sintered compact calcinated and obtained by coincidence, and was formed in the front flesh-side principal plane of the above-mentioned layered product, and is characterized by coming to polarize all ceramic layers in the same direction in the thickness direction.

[Claim 5] The above-mentioned layered product is formed in rectangle tabular, and it holds in the case where the above-mentioned layered product has opening on the inferior surface of tongue, and has a sound emission hole on the top face. Two sides which the above-mentioned layered product counters are supported by the supporting agent by the supporter formed in the medial-surface opposite section of the above-mentioned case. The closure of the clearance between other two sides of the above-mentioned layered product and the medial surface of the above-mentioned case is carried out with elastic encapsulant. The piezo-electric mold electroacoustic transducer according to claim 1 to 4 characterized by being closed with the back lid with which the opening of the above-mentioned case has the electrode for external connection connected to the principal plane electrode and internal electrode of the above-mentioned layered product.

[Claim 6] The above-mentioned layered product is formed in rectangle tabular, and the above-mentioned layered product has opening on the top face. It holds in

the case where it has the electrode for external connection connected to the

principal plane electrode and internal electrode of the above-mentioned layered product. Two sides which the above-mentioned layered product counters are fixed to the supporter formed in the medial-surface opposite section of the above-mentioned case by the supporting agent. The piezo-electric mold electroacoustic transducer according to claim 1 to 4 which the closure of the clearance between other two sides of the above-mentioned layered product and the inside of the above-mentioned case is carried out with elastic encapsulant, and is characterized by closing top-face opening of the above-mentioned case by the top cover which has a sound emission hole.

[Claim 7] The above-mentioned layered product is formed in rectangle tabular, and it holds in the case where the above-mentioned layered product has opening on the inferior surface of tongue, and has a sound emission hole on the top face. Four sides of the above-mentioned layered product are fixed to the supporter formed in the medial surface of the above-mentioned case by the supporting agent. The piezo-electric mold electroacoustic transducer according to claim 1 to 4 characterized by being closed with the back lid with which the opening of the above-mentioned case has the electrode for external connection connected to the principal plane electrode and internal electrode of the above-mentioned layered product.

[Claim 8] The above-mentioned layered product is formed in rectangle tabular, and the above-mentioned layered product has opening on the top face. It holds in the case where it has the electrode for external connection connected to the principal plane electrode and internal electrode of the above-mentioned layered product. The piezo-electric mold electroacoustic transducer according to claim 1 to 4 with which four sides of the above-mentioned layered product are fixed to the supporter formed in the medial surface of the above-mentioned case by the supporting agent, and top-face opening of the above-mentioned case is characterized by being closed by the top cover which has a sound emission hole.

#### \* NOTICES \*

JPO and NCIPI are not responsible for any damages caused by the use of this translation.

- 1. This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.\*\*\*\* shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

### **DETAILED DESCRIPTION**

[Detailed Description of the Invention]

[0001]

[Field of the Invention] This inventions are piezo-electric mold electroacoustic transducers, such as a piezo-electric earphone, a piezo-electric sounder, a piezo-electric loudspeaker, and a piezo-electric buzzer, and a thing especially about the structure of the diaphragm.

[0002]

[Description of the Prior Art] Conventionally, the piezo-electric mold electroacoustic transducer is widely used for the piezo-electric earphone, the piezo-electric buzzer, etc. This kind of piezo-electric mold electroacoustic transducer has the common thing of the structure which stuck the circular metal plate on one side of a piezo-electric circular ceramic plate, constituted the unimorph mold diaphragm, supported the periphery section of this diaphragm in the circular case, and closed opening of a case with covering. However, since in the case of a uni-morph mold diaphragm the ceramic plate which an outer diameter expands and contracts is pasted up on the metal plate which does not carry out a dimensional change and crookedness vibration is obtained by electrical-potential-difference impression, there is a fault of being small, the amount of displacement, i.e., sound pressure.

[0003] Then, the bimorph mold diaphragm of a laminated structure which consists of two or more electrostrictive ceramics layers is proposed (JP,61-205100,A). This diaphragm carried out the laminating of two or more ceramic green sheet and two or more electrodes, and the sintered compact calcinated and obtained by coincidence was used for it, and it has connected inter-electrode electrically by the through hole formed in the location which does not restrain vibration of a diaphragm. And compared with a uni-morph mold, the amount of big displacement, i.e., big sound pressure, can be obtained with constituting so that the 1st and 2nd oscillating fields arranged in order in the thickness direction may vibrate to hard flow mutually.

[0004]

[Problem(s) to be Solved by the Invention] However, after connecting the electrode of one principal plane, and one internal electrode mutually through the through hole and connecting the principal plane electrode of another side, and the internal electrode of another side mutually through a through hole as shown in Fig. 17 of the above-mentioned official report when crookedness vibration of the diaphragm which becomes in the case of the above-mentioned bimorph mold diaphragm (for example, a three-layer ceramic layer) tended to be carried out, it is necessary to impress an alternation electrical potential difference among both. Therefore, the complicated interconnect between a principal plane electrode and an internal electrode may have been needed, and it may have become cost quantity.

[0005] Moreover, also when performing polarization processing to the above-mentioned layered product, an electrical potential difference must be impressed and polarized between an internal electrode and the principal plane electrode of a front flesh side. For example, in the case of the diaphragm of a three-tiered structure, as shown in Fig. 14 of the above-mentioned official report, between a bond, this electrode for connection, and the principal plane electrode of a front flesh side, the high voltage is impressed and an internal electrode and two through holes through which it flows are polarized with the electrode for

connection. Thus, in the case of the conventional bimorph mold diaphragm, the internal electrode needed to be pulled out outside through the through hole for polarization processing, and there was a fault of needing the complicated processing of forming the electrode for connection etc.

[0006] Then, the purpose of this invention loses interconnect with a principal plane electrode and an internal electrode, and is to obtain the piezo-electric mold electroacoustic transducer which can constitute a bimorph mold diaphragm from easy connection structure. Moreover, other purposes are to obtain the piezo-electric mold electroacoustic transducer which can perform polarization processing easily.

### [0007]

[Means for Solving the Problem] In order to attain the above-mentioned purpose, invention according to claim 1 Carry out the laminating of two-layer or the threelayer electrostrictive ceramics layer, and a layered product is formed. A principal plane electrode is formed in the front flesh-side principal plane of this layered product, and an internal electrode is formed between each ceramic layer. In the thickness direction, polarization of all the ceramic layers is carried out in the same direction, it is impressing an alternation signal between the abovementioned principal plane electrode and an internal electrode, and the abovementioned layered product offers the piezo-electric mold electroacoustic transducer characterized by producing crookedness vibration as a whole. [0008] If an alternation electrical potential difference is impressed between a principal plane electrode and an internal electrode in the case of the layered product of this invention, the direction of electric field committed in the ceramic layer on a side front and a background will turn into hard flow in the thickness direction. On the other hand, all ceramic layers have turned to the direction of polarization in the same direction in the thickness direction. Electrostrictive ceramics has the property shrunken in the direction of a flat surface, if the direction of polarization and the direction of electric field are the same directions, and if the direction of polarization and the direction of electric field are hard flow,

it has the property extended in the direction of a flat surface. Therefore, when impressing the alternation electrical potential difference as mentioned above and the ceramic layer on a side front is prolonged, the ceramic layer on a background will be shrunken and a layered product will produce crookedness vibration as a whole. Since this amount of displacement becomes large compared with a unimorph mold diaphragm, sound pressure also increases.

[0009] In this invention, if the principal plane electrode of a front flesh side is connected mutually and an alternation electrical potential difference is impressed between this and an internal electrode, since crookedness vibration can be generated, the complicated interconnect between a principal plane electrode and an internal electrode becomes unnecessary like before, structure becomes easy, and processing cost can be reduced.

[0010] It is desirable to connect an internal electrode with the end-face electrode formed in the end face of a layered product like claim 2, and to impress an alternation signal between the above-mentioned end-face electrode and two principal plane electrodes. In this case, exceptional processing of a through hole etc. is not needed.

[0011] Like claim 3, when the layered product consists of three-layer ceramic layers, it is desirable to make thickness of a middle ceramic layer into 50% - 80% of the thickness of the whole layered product. Although what is necessary is just to increase the number of laminatings of a layered product in order to raise sound pressure, when thickness is being fixed by resonance frequency, the number of laminatings cannot be increased freely, either. Since there is no potential difference between two internal electrodes in the case of the layered product of a three-tiered structure, an interlayer will not contribute to crookedness vibration but only the ceramic layer on a side front and a background will carry out crookedness vibration. A ceramic layer has so large that the thickness is thin the amount of displacement. Then, if the thickness of the whole layered product is set constant and an interlayer's thickness is relatively thickened to the thickness of a front lining, the thickness of the ceramic layer on the side front

which contributes to crookedness vibration, and a background will become thin relatively, and the big amount of displacement will be obtained. In addition, if an interlayer's thickness is enlarged too much, the thickness of a front lining will become thin too much, reinforcement will fall, and a big variation rate will not be obtained. Then, big sound pressure can be obtained by making an interlayer's thickness into 50% - 80% of the whole range.

[0012] It is impressing an electrical potential difference to the principal plane inter-electrode which consisted of a sintered compact with which a layered product's carries out the laminating of the ceramic green sheet of two-layer or three layers through an electrode layer, calcinates it to coincidence, and is obtained like claim 4, and was formed in the front flesh-side principal plane of a layered product, and it is desirable to polarize all ceramic layers in the same direction in the thickness direction. That is, although it is also possible to carry out two or more sheet laminating adhesion of the ceramic plate which calcinated beforehand and carried out polarization processing, and to obtain a layered product, now, thickness of a layered product cannot be made thin but sound pressure is small. On the other hand, if an electrode layer is carried out in between, and the laminating of the ceramic green sheet is carried out and it carries out coincidence baking, a very thin layered product can be obtained and high sound pressure can be obtained. And since the direction of polarization of each ceramic layer of a layered product has turned to the same direction, polarization processing becomes very easy that the polarization processing does not need to impress an electrical potential difference between an internal electrode and a principal plane electrode like before, and should just impress an electrical potential difference between the principal plane electrodes of a front flesh side.

[0013] When holding the above-mentioned layered product in housing and using as the sounding body like a piezo-electric earphone or a piezo-electric sounder, it can consider as structure [like] according to claim 5 to 8. That is, claims 5 and 6 are the examples suitable for the application as an earphone, and since they

correspond to the frequency of a large range, they are used in fields other than a resonance field. Therefore, since the vibrational energy of a layered product is comparatively small, only two sides which a layered product counters are supported in a case, and two sides have structure closed free [ displacement with an elastic closure object ] for others. On the other hand, claims 7 and 8 are the examples suitable for the application of a piezo-electric sounder etc., and since they correspond to the amount of Oto in single frequency, they are used in a resonance field. In this case, since the vibrational energy of a layered product is very large, it has structure which supported all four sides of a layered product in the case. Since the principal plane electrode and internal electrode of a layered product can be pulled out to the exterior of housing, without using lead wire, any structure can constitute them as a surface mounted device.

[0014]

[Embodiment of the Invention] Drawing 1 and drawing 2 show the 1st example of the piezo-electric mold electroacoustic transducer concerning this invention. This piezo-electric mold electroacoustic transducer consists of a disc-like diaphragm (layered product) 1, and the circular case 10 and the back lid 11 which held this diaphragm 1. The sound emission hole 12 was formed in the top face of a case 10, and the back lid 11 has pasted the opening. The terminals 13 and 14 for external connection were fixed to the position of symmetry of the periphery section of a case 10 in insert molding etc., and some terminals 13 and 14 are exposed inside a case 10. The electrode of a diaphragm 1 is electrically connected to the inside outcrop of terminals 13 and 14 by electroconductive glue 15 and 16. In addition, the closure of the clearance between the periphery section of diaphragms 1 other than the part which applied electroconductive glue 15 and 16, and a case 10 is carried out with elastic encapsulants (not shown), such as silicone rubber.

[0015] A diaphragm 1 carries out the laminating of the two-layer electrostrictive ceramics layers 2 and 3 which consist of PZT etc., as shown in drawing 3 and drawing 4, the principal plane electrodes 4 and 5 are formed in the front flesh-

side principal plane of a diaphragm 1, and the internal electrode 6 is formed among the ceramic layers 2 and 3. As a thick wire arrow head shows to drawing 4, in the thickness direction, polarization of the two ceramic layers 2 and 3 is carried out in the same direction.

[0016] In this example, the principal plane electrode 4 on a side front and the principal plane electrode 5 on a background are formed in a round shape a little smaller than the diameter of a diaphragm 1, and those drawer electrodes 4a and 5a are pulled out to the periphery edge of a diaphragm 1. It is mostly formed in a symmetry configuration with the principal plane electrodes 4 and 5, drawer electrode 6a of an internal electrode 6 is mostly pulled out with the abovementioned drawer electrodes 4a and 5a to the position of symmetry, and the internal electrode 6 is connected to the end-face electrode 7 prepared in the end face. In addition, some end-face electrodes 7 are pulled out to the front rear face of a diaphragm 1. The above-mentioned drawer electrodes 4a and 5a are connected with a terminal 13 by electroconductive glue 15, and the end-face electrode 7 is connected with the terminal 14 by electroconductive glue 16. And crookedness vibration of the diaphragm 1 can be carried out by impressing a predetermined alternation electrical potential difference among terminals 13 and 14.

[0017] For example, if the electrical potential difference of minus and the electrical potential difference of plus to the other-end child 14 are impressed to one terminal 13, the electric field of the direction shown by the thin line arrow head of drawing 4 will arise. Since the ceramic layers 2 and 3 have the property shrunken in the direction of a flat surface if the direction of polarization and the direction of electric field are the same directions, and it has the property extended in the direction of a flat surface if the direction of polarization and the direction of electric field are hard flow, the ceramic layer 2 on a side front will be shrunken and the ceramic layer 3 on a background will be extended. Therefore, a diaphragm 1 is crooked so that a core may serve as a convex to a lower part. An alternation electrical potential difference, then a diaphragm 1 can produce

crookedness vibration for the electrical potential difference impressed to terminals 13 and 14 periodically, and the sound of big sound pressure can be generated by this.

[0018] The diaphragm 1 which consists of the above-mentioned configuration is manufactured by the following approaches. That is, an electrode layer is formed in the front face of the ceramic green sheet of a mother substrate condition at a pattern predetermined by technique, such as printing, the laminating of this one ceramic green sheet and the one ceramic green sheet which does not form the electrode layer is carried out, and it is stuck by pressure. Next, it pierces or cuts into the configuration corresponding to a diaphragm 1 from this layered product. Next, coincidence baking of punching or the cut layered product is carried out, and a sintering layered product is obtained. Next, a principal plane electrode is formed in the front flesh-side principal plane of a sintering layered product, and all the ceramic layers that constitute a layered product are polarized in the same direction in the thickness direction by impressing polarization voltage to these principal plane inter-electrode. Then, the end-face electrode 7 etc. is formed and a diaphragm 1 is obtained.

[0019] By the above-mentioned manufacture approach, after piercing the ceramic green sheet of the mother substrate condition by which the laminating was carried out in an individual configuration, it calcinated and polarization processing was carried out after that, but after calcinating the ceramic green sheet by which the laminating was carried out, polarization processing may be carried out in the state of a mother substrate, and you may cut into an individual configuration by after that. In this case, what is necessary is just to use well-known approaches, such as laser processing, in order to cut a sintered compact.

[0020] Drawing 5 and drawing 6 show the 2nd example of the piezo-electric mold electroacoustic transducer concerning this invention. Although the electrode of a diaphragm 1 was pulled out to the exterior in drawing 1 and drawing 2 using the terminals 13 and 14 fixed to the case 10, lead wire 20 and 21 is used in drawing 5 and drawing 6. In this case, lead wire 20 and 21 is connected to the principal

plane electrode 5 and the end-face electrode 7 by the side of the rear face of a diaphragm 1 by cement 22 and 23, such as solder and electroconductive glue, respectively. Therefore, the principal plane electrodes 4 and 5 of a front flesh side may be mutually connected using electroconductive glue, and the principal plane electrodes 4 and 5 may be beforehand connected with an end-face electrode.

[0021] Drawing 7 and drawing 8 show the 3rd example of the piezo-electric mold electroacoustic transducer concerning this invention. This piezo-electric mold electroacoustic transducer consists of a rectangular diaphragm (layered product) 30, and the case 40 and the back lid 41 of the square shape which held this diaphragm 30. The sound emission hole 42 was formed in the top face of a case 40, and the back lid 41 has pasted the opening. The level difference-like supporters 42a and 42b are formed in the medial surface of two sides which a case 40 counters, and two sides by the side of the shorter side of a diaphragm 30 are supported by the supporting agents 43a and 43b, such as adhesives, on these supporter 42a and 42b. The braking hole 48 is formed in a different side face from the side face in which the supporters 42a and 42b of a case 40 were formed. Moreover, the closure of the clearance between two sides and cases 40 by the side of the long side of a diaphragm 30 is carried out with the elastic encapsulants 44a and 44b, such as silicone rubber. The electrodes 45a and 45b for external connection are formed in the both-ends table rear face of the back lid 41, and the electrodes 45a and 45b of a front flesh side have flowed mutually through the inside of the through hole slots 46a and 46b formed in the both-ends side edge of the back lid 41.

[0022] While the electrodes 45a and 45b for external connection and the electrode of a diaphragm 30 are mutually connected by slushing electroconductive glue 47a and 47b from the through hole slots 46a and 46b as shown in drawing 8 after pasting up the back lid 41 on the opening of a case 40, the through hole slots 46a and 46b are closed. Thereby, a piezo-electric mold electroacoustic transducer is completed.

[0023] As shown in drawing 9 and drawing 10, as for the diaphragm 30 of this example, the laminating of the two-layer electrostrictive ceramics layers 31 and 32 is carried out, the principal plane electrodes 33 and 34 are formed in the front flesh-side principal plane of a diaphragm 30, and the internal electrode 35 is formed among the ceramic layers 31 and 32. As a thick wire arrow head shows to drawing 10, in the thickness direction, polarization of the two ceramic layers 31 and 32 is carried out in the same direction.

[0024] In this example, the principal plane electrode 33 on a side front and the principal plane electrode 34 on a background are the shorter sides and these width of face of a diaphragm 30, and are formed a little shorter than a long side, and that end is connected to the end-face electrode 36 formed in one shorter side side edge side of a diaphragm 30. Therefore, the principal plane electrodes 33 and 34 of a front flesh side are connected mutually. The internal electrode 35 was mostly formed in the symmetry configuration with the principal plane electrodes 33 and 34, it is separated from the end of an internal electrode 35 of the internal electrode with the above-mentioned end-face electrode 36, and the other end is connected to the end-face electrode 37 formed in the shorter side side edge side of another side of a diaphragm 30. In addition, the end-face electrode 37 and the flowing narrow width auxiliary electrode 38 are formed in the vertical side of the shorter side side edge section of another side of a diaphragm 30.

[0025] The above-mentioned end-face electrode 36 or the principal plane electrode 34 on a background is connected with electrode 45a for external connection by electroconductive glue 47a like drawing 8, and the end-face electrode 37 is connected with electrode 45b for external connection by electroconductive glue 47b. And crookedness vibration of the diaphragm 30 can be carried out in die-length bending mode by impressing a predetermined alternation electrical potential difference among the electrodes 45a and 45b for external connection. That is, crookedness vibration can be carried out, being able to use the shorter side side both ends of a diaphragm 30 as the supporting point,

and being able to use the center section of the longitudinal direction as a maximum amplitude point.

[0026] Since only a core serves as a maximum amplitude point, in the case of a circular diaphragm 1 like the 1st example, the displacement volume is small, and sound conversion efficiency is comparatively low to it. Moreover, since the perimeter of a diaphragm 1 is restrained, a radius dimension will become large, if a frequency tends to become high and it is going to obtain the piezo-electric diaphragm of a low frequency. On the other hand, since in the case of a rectangle diaphragm 30 like the 3rd example a maximum amplitude point meets the center line of the die-length direction and exists, the displacement volume is large and high sound conversion efficiency can be acquired. Moreover, although the die-length direction both ends are fixed, since a diaphragm 30 can displace a part in the meantime freely with the elastic encapsulants 44a and 44b, it can obtain a low frequency compared with a circular diaphragm. On the contrary, a dimension can be miniaturized if the same frequency is obtained.

[0027] Drawing 11 shows the 4th example of a diaphragm which is a modification of drawing 10. Although drawing 10 showed the example whose internal electrode 35 is a partial electrode, in drawing 11, it considers as a whole surface electrode. In this case, since the internal electrode 35 is prolonged in the end-face electrode 36 side, there is a possibility that an internal electrode 35 and the end-face electrode 36 may flow. Then, an insulating layer 39 is first formed in the end face of diaphragm 30', and the end-face electrode 36 which makes it flow through the principal plane electrodes 33 and 34 of a front flesh side is formed on it. Thereby, even when an internal electrode 35 is used as a whole surface electrode, an internal electrode 35 and the principal plane electrodes 33 and 34 can be insulated certainly.

[0028] Drawing 12 shows the 5th example of a diaphragm. The diaphragm 50 of this example carries out the laminating of the three-layer electrostrictive ceramics layers 51-53, the principal plane electrodes 54 and 55 are formed in the front rear face of a diaphragm 50, and internal electrodes 56 and 57 are formed among

each ceramic layers 51-53. As a thick wire arrow head shows, in the thickness direction, polarization of the three ceramic layers 51-53 is carried out in the same direction.

[0029] The principal plane electrodes 54 and 55 of this example are the shorter sides and these width of face of a diaphragm 50 like drawing 10 R> 0, and are formed a little shorter than a long side, and that end is connected to the end-face electrode 58 formed in one shorter side side edge side of a diaphragm 50. Therefore, the principal plane electrodes 54 and 55 of a front flesh side are connected mutually. It is separated from the end of internal electrodes 56 and 57 with the end-face electrode 58, and the other end is connected to the end-face electrode 59 formed in the shorter side side edge side of another side of a diaphragm 50. Therefore, internal electrodes 56 and 57 are also connected mutually. In addition, the end-face electrode 59 and narrow width auxiliary-electrode 59a through which it flows are formed in the vertical side of the shorter side side edge section of another side of a diaphragm 50.

[0030] For example, if the electrical potential difference of minus and the electrical potential difference of plus in the end-face electrode 59 are impressed to the end-face electrode 58, the electric field of the direction shown by the thin line arrow head of drawing 12 will arise. Since the internal electrodes 56 and 57 located in the both sides of the ceramic layer 52 which is an interlayer at this time are the same potentials, electric field do not produce them. Since the direction of polarization and the direction of electric field are the same directions, the ceramic layer 51 on a side front is shrunken in the direction of a flat surface, and since the direction of polarization and the direction of electric field are hard flow, the ceramic layer 52 on a background is extended in the direction of a flat surface. And an interlayer 52 is not expanded and contracted. Therefore, a diaphragm 50 is crooked so that it may become a convex to a lower part. If an alternation electrical potential difference is impressed between the end-face electrode 58 and 59, a diaphragm 50 can produce crookedness vibration periodically and can generate the sound of big sound pressure by this. In addition, in drawing 12,

although internal electrodes 56 and 57 were used as the partial electrode, it is good also as a whole surface electrode like drawing 11.

[0031] It is the same as that of the manufacture approach of the diaphragm 1 of two-layer structure which also showed the above manufacture approaches of the diaphragm 50 of a three-tiered structure in drawing 4. That is, an electrode layer is formed in the front face of the ceramic green sheet of a mother substrate condition at a pattern predetermined by technique, such as printing, the threesheet laminating of this ceramic green sheet is carried out, and it is stuck by pressure. It pierces or cuts into the configuration corresponding to a diaphragm 50 from this layered product, coincidence baking of this punching or cut layered product is carried out, and a sintering layered product is obtained. Next, the principal plane electrodes 54 and 55 are formed in the front rear face of a sintering layered product, and all the ceramic layers 51-53 that constitute a layered product are polarized in the same direction in the thickness direction by impressing polarization voltage to these principal plane inter-electrode. Then, a diaphragm 50 is obtained by forming the end-face electrodes 58 and 59 etc. Since what is necessary is just not to connect internal electrodes 56 and 57 and the principal plane electrodes 54 and 55 mutually on the occasion of polarization in this case, and to impress an electrical potential difference between the principal plane electrode 54 of a front flesh side, and 55, polarization processing is easy.

[0032] Drawing 13 shows the 6th example of a diaphragm. Although the example of drawing 12 R> 2 showed the example whose three-layer ceramic layers 51-53 are the same thickness mostly, in drawing 13, the middle ceramic layer 52 is thickened compared with the ceramic layers 51 and 53 of a front flesh side. As for especially the thickness of the middle ceramic layer 52, it is desirable to carry out to 50% - 80% of the thickness of whole diaphragm 50'. In addition, since other structures are the same as that of drawing 12, duplication explanation is omitted.

[0033] Drawing 14 shows change of the sound pressure when changing the rate

of the thickness of the middle ceramic layer 52. An axis of ordinate is the ratio of the sound pressure when setting sound pressure of the diaphragm (refer to drawing 10) of two-layer structure to 1, and an axis of abscissa expresses the rate of the thickness of the middle ceramic layer 52 to the thickness of whole diaphragm 50'. In addition, sound pressure was measured on the conditions that applied voltage is certain, uniformly [ the thickness of whole diaphragm 50' ]. [0034] It turns out that sound pressure rises compared with two-layer in the case of three layers so that clearly from drawing 14. Moreover, when an interlayer's thickness is made into 50% - 80% of the whole compared with the case (33%) where all three layers are the same thickness, sound pressure rises further. When an interlayer's thickness is especially made into 60% - 70% of the whole, the greatest sound pressure (it compares with two-layer and they are 1.6 times) can be obtained. Therefore, when the number of laminatings has constraint, sound pressure can be raised by enlarging an interlayer's thickness to the maximum, lessening the number of laminatings (three layers). [0035] Drawing 15 - drawing 17 are the 7th example of the piezo-electric mold electroacoustic transducer concerning this invention, and show the example constituted as a piezo-electric earphone of a surface mount mold. This piezoelectric earphone consists of a diaphragm (layered product) 30 of a profile and a rectangle, a case 60 of the square shape which held this diaphragm 30, and a top cover 68 that has the sound emission hole 69. Since the diaphragm 30 is the same as that of what was shown in drawing 9 and drawing 10, it has attached the same sign. A case 60 is formed with heat resistant resin, such as LCP (liquid crystal polymer), SPS (syndiotactic polystyrene), PPS (polyphenylene sulfide), and epoxy, and the top cover 68 is also formed with a heat-resistant ingredient or ceramics, such as a liquid crystal polymer or glass epoxy. Opening 61 was formed in the top face of a case 60, and the top cover 68 has pasted this top-face opening 61. The level difference-like supporters 62a and 62b are formed in the medial surface of two sides which a case 60 counters, and insert molding of the electrodes 63a and 63b for external connection is carried out so that it may

expose to the top face of these supporters 62a and 62b, and the lateral surface of a case 60. It consists of metal terminals which consist of Au, a Cu alloy which performed Sn plating, Fe, etc. as these electrodes 63a and 63b for external connection, for example. The braking hole 64 is formed in a different side face from the side face in which the supporters 62a and 62b of a case 60 were formed. [0036] Two sides by the side of the shorter side of a diaphragm 30 are supported by the supporting agents 65a and 65b, such as adhesives, on supporter 62a and 62b. Moreover, the closure of the clearance between two sides and cases 60 by the side of the long side of a diaphragm 30 is carried out with the elastic encapsulants 66a and 66b, such as silicone rubber. And the end-face electrodes 36 and 37 prepared in two sides by the side of the shorter side of a diaphragm 30 are electrically connected with the electrodes 63a and 63b for external connection exposed to the top face of Supporters 62a and 62b by conductive paste 67a and 67b, respectively. In addition, it is better to perform it, after spreading of supporting agents 65a and 65b and the elastic encapsulants 66a and 66b pastes up a diaphragm 30 and the electrodes 63a and 63b for external connection by conductive paste 67a and 67b. And heat hardening of conductive paste 67a and 67b, supporting agents 65a and 65b, and the elastic encapsulants 66a and 66b may be performed to coincidence.

[0037] Drawing 18 is the 8th example of the piezo-electric mold electroacoustic transducer concerning this invention, and is the modification of the example shown in drawing 15 - drawing 17 . In this example, it was not inserted to a case 60, and the electrodes 63a and 63b for external connection insert in hole 60a of a case 60 the metal terminal formed in another object, and paste up. Since other structures are the same as that of drawing 15 R> 5 - drawing 17, they give the same sign to the same components, and omit explanation.

[0038] Drawing 19 - drawing 21 are the 9th example of the piezo-electric mold electroacoustic transducer concerning this invention, and show the example constituted as surface mount die parts. In this example, it replaces with the electrodes 63a and 63b for external connection which consist of an insertion

terminal in drawing 15 - drawing 17, and considers as the electrode layers 63c and 63d formed by the dry type galvanizing methods, such as the non-electrolyzed wet galvanizing method or a spatter. In this example, from the external surface of the flank which formed the supporters 62a and 62b of a case 60, electrode layers 63c and 63d are missing from the top face of Supporters 62a and 62b, and are formed continuously. Since other configurations are the same as that of the thing of drawing 15 - drawing 17, they give the same sign to the same components, and omit explanation.

[0039] In addition, in the example shown in drawing 15 - drawing 21, it is possible as a diaphragm not only the diaphragm 30 shown in drawing 9 and drawing 10 but diaphragm 30' shown in drawing 11, drawing 12, and drawing 13 and to also use 50 and 50'.

[0040] Drawing 22 is the 10th example of the piezo-electric mold electroacoustic transducer concerning this invention. This example is a modification of the example shown in drawing 7, gives the same sign to the same part as drawing 7, and omits explanation. Drawing 22 is the perspective view seen from the background, and the level difference-like supporter 42 is formed in the medialsurface perimeter of case 40'. The top face of these supporters 42 is formed in the same height, and the four-side perimeter of a diaphragm 30 is supported by the supporting agents 43, such as adhesives, on the supporter 42. Although it is used as a sound producing device in the single frequency of for example, a piezo-electric sounder etc. and the perimeter of a diaphragm 30 is restrained by the supporting agent 43, by using a diaphragm 30 in a resonance field, this example can be excited strongly and can obtain the amount of Oto. [0041] Drawing 23 is the 11th example of the piezo-electric mold electroacoustic transducer concerning this invention. This example has the almost same structure as the example shown in drawing 15 - Fig. 1717, gives the same sign to drawing 15 - Fig. 1717 and an intersection, and omits explanation. In this example, the level difference-like supporter 62 is formed in the medial-surface perimeter of the case 60 of a square shape, and all four sides of a diaphragm 30 are supported by the supporting agents 65, such as adhesives, to the supporter 62. This example is also an example used as a sound producing device in the single frequency of a piezo-electric sounder etc., and a diaphragm 30 is used in a resonance field.

[0042] This invention is not limited to the above-mentioned example, and can be variously changed in the range which does not deviate from the meaning of this invention. Although an internal electrode and the flowing end-face electrode are formed in the end face of a diaphragm and it was made to pull out to the exterior through this end-face electrode in the above-mentioned example, it does not restrict to this. That is, an internal electrode may be pulled out to the exterior through a through hole like JP,61-205100,A, and you may pull out to the exterior through slit-like a slot or a hole. Although the manufacture approaches of 50 and 50' are the diaphragms 1 and 30 of the above-mentioned example, 30', and a thing that carries out polarization processing of this sintering layered product for a ceramic green sheet through an electrode layer two sheets or after carrying out a three-sheet laminating, carrying out coincidence baking of this layered product and obtaining a sintering layered product, they may be replaced with this approach and may carry out laminating adhesion of two sheets or the three electrostrictive ceramics plates which calcinated beforehand and carried out polarization processing. however, since the thickness of a diaphragm is boiled markedly, and the manufacture approach of the former calcinated behind a laminating can make it thin compared with the approach of the latter which carries out the laminating of what was calcinated beforehand and can enlarge sound pressure, it can obtain the diaphragm the direction of the former manufacture approach excelled [diaphragm] in sound conversion efficiency The diaphragm of this invention may stick reinforcement sheets, such as a metal film and a resin sheet, on one side of what [ not only ] consisted of only electrostrictive ceramics layers but a layered product. However, this reinforcement sheet is for preventing the crack of a layered product etc. unlike the metal plate of a uni-morph mold diaphragm, and what does not check

crookedness vibration of a layered product is desirable. [0043]

[Effect of the Invention] By the above explanation, according to invention according to claim 1, a principal plane electrode is formed in the front rear face of a layered product which consists of two-layer or a three-layer electrostrictive ceramics layer so that clearly. Since the internal electrode was formed between each ceramic layer and all the ceramic layers were polarized in the same direction in the thickness direction The ceramic layer on a side front and a background will expand and contract to hard flow, and if an alternation signal is impressed between a principal plane electrode and an internal electrode, a layered product will produce crookedness vibration as a whole. Since this amount of displacement becomes large compared with a uni-morph mold diaphragm, sound pressure also increases. Moreover, since polarization of all the ceramic layers is carried out in the same direction in the thickness direction, the complicated interconnect between the principal plane electrodes and internal electrodes like before is unnecessary, structure is [ that what is necessary is just to impress an alternation signal between a principal plane electrode and an internal electrode I easy, and a manufacturing cost can be reduced.

[Translation done.]

\* NOTICES \*

JPO and NCIPI are not responsible for any damages caused by the use of this translation.

- 1. This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.\*\*\*\* shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

#### **DESCRIPTION OF DRAWINGS**

[Brief Description of the Drawings]

[Drawing 1] It is the appearance perspective view of the 1st example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Drawing 2] It is drawing of longitudinal section of the piezo-electric mold electroacoustic transducer shown in drawing 1.

[Drawing 3] It is the perspective view of the diaphragm used for the piezo-electric mold electroacoustic transducer of drawing 1.

[Drawing 4] It is drawing of longitudinal section of the diaphragm shown in drawing 3.

[Drawing 5] It is the appearance perspective view of the 2nd example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Drawing 6] It is drawing of longitudinal section of the piezo-electric mold electroacoustic transducer shown in drawing 5.

[Drawing 7] It is the decomposition perspective view which looked at the 3rd example of the piezo-electric mold electroacoustic transducer concerning this invention from the background.

[Drawing 8] It is the sectional view of the piezo-electric mold electroacoustic transducer of drawing 7.

[Drawing 9] It is the perspective view of the diaphragm used for the piezo-electric mold electroacoustic transducer of drawing 7.

[Drawing 10] It is the sectional view of the diaphragm of drawing 9.

[Drawing 11] It is the sectional view of the 4th example of the diaphragm concerning this invention.

[Drawing 12] It is the sectional view of the 5th example of the diaphragm concerning this invention.

[Drawing 13] It is the sectional view of the 6th example of the diaphragm concerning this invention.

[Drawing 14] It is the property Fig. showing the relation between the thickness of

the interlayer of the piezo-electric mold electroacoustic transducer using the diaphragm shown in drawing 13, and sound pressure.

[Drawing 15] It is the perspective view of the 7th example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Drawing 16] It is the decomposition perspective view of the piezo-electric mold electroacoustic transducer shown in drawing 15.

[Drawing 17] It is the A-A line sectional view of drawing 15.

[Drawing 18] It is the decomposition perspective view of the 8th example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Drawing 19] It is the perspective view of the 9th example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Drawing 20] It is the decomposition perspective view of the piezo-electric mold electroacoustic transducer shown in drawing 19.

[Drawing 21] It is the B-B line sectional view of drawing 19.

[Drawing 22] It is the decomposition perspective view of the 10th example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Drawing 23] It is the decomposition perspective view of the 11th example of the piezo-electric mold electroacoustic transducer concerning this invention.

[Description of Notations]

1, 30, 30', 50, 50' Diaphragm

2, 3, 31, 32, 51-53 Ceramic layer

4, 5, 33, 34, 54, 55 Principal plane electrode

6, 35, 56, 57 Internal electrode

10 60 Case

11 [] Back Lid

62a, 62b Supporter

63a, 63b Electrode for external connection

65a, 65b Supporting agent

66a, 66b Elastic encapsulant

67a, 67b Conductive paste

### [Translation done.]


\* NOTICES \*

JPO and NCIPI are not responsible for any damages caused by the use of this translation.


- 1. This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.\*\*\*\* shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

### **DRAWINGS**


### [Drawing 1]





### [Drawing 2]





### [Drawing 3]













### [Drawing 8]




### [Drawing 9]




## [Drawing 13]




### [Drawing 15]







[Drawing 19]



### [Drawing 10]




### [Drawing 11]




### [Drawing 12]




### [Drawing 14]




[Drawing 16]




[Drawing 18]





[Drawing 20]




[Drawing 21]







[Drawing 23]



(19) 日本国特許庁 (JP)

### (12) 公開特許公報(A)

(11)特許出願公開發号 特開2001-95094 (P2001-95094A)

(43)公開日 平成13年4月6日(2001.4.6)

(51) Int.CL.	識別記号	FI	デーマコート*(参考)
H04R 17/00		H04R 17/00	
HO1L 41/09		HO1L 41/08	U
			C

#### 審査請求 未請求 請求項の数8 OL (全 10 頁)


(ar) (het al t	4±5±0000 000000 000000	(C1) ILINES (	000000191
(21)出顧番号	特顧2000-207729(P2000-207729)	(71)出廢人	
			株式会社村田製作所
(22)出験日	平成12年7月10日(2000.7.10)		京都府長岡京市天神二丁目26番10号
		(72) 発明者	竹島 哲夫
(31)優先権主張番号	特醫平11-207198		京都府長岡京市天神2丁目26番10号 株式
(32)優先日	平成11年7月22日(1999.7.22)		会社村田製作所内
(33)優先權主張国	日本 (JP)	(72) 発明者	<b>岸本 健樹</b>
			京都府長岡京市天神2丁目26番10号 株式
			会社村田製作所內
		(74)代理人	
		(14/104:)(	
			弁理士 筒井 秀隆
			最終頁に続く

#### (54) 【発明の名称】 圧電型電気音響変換器

#### (57)【要約】

【課題】主面電極と内部電極との相互接続をなくし、簡 単な接続構造でバイモルフ型振動板を構成できる圧電型 電気音響変換器を得る。

【解決手段】2層または3層の圧電をラミックス層3 1、32を補層して補層体が形成され、この補層体の表 裏面には主面電優33,34が形成され、各セラミック ス層31,32の間には内部電極35が形成される。す べてのセラミックス層31、32は厚み方向において同 一方向に分極されており、主面弯極33、34と内部弯 極3.5 との間に交番信号を印加することで、領層体は全 体として屈曲振動を生じる。



特闘2001-95094

(2)

#### 【特許請求の範囲】

【請求項1】2層または3層の圧電セラミックス層を綺 層して綺層体が形成され、この綺層体の表裏主面には主 面電極が形成され、各セラミックス層の間には内部電極 が形成され、すべてのセラミックス層は厚み方向におい て同一方向に分極されており、上記主面穹径と内部穹径 との間に交替信号を印加することで、上記請應体は全体 として屈曲振動を生じることを特徴とする圧電型電気音 紧变换器。

1

【請求項2】上記内部電極は補層体の端面に形成された 10 端面電極と接続され、上記端面電極と2つの主面電極と の間に交番信号が印加されることを特徴とする請求項! に記載の圧電型電気音響変換器。

【請求項3】上記論層体は3層のセラミックス層で構成 され、中間のセラミックス層の厚みは、綺層体の全体の 厚みの50%~80%であることを特徴とする請求項1 または2に記載の圧電型電気音響変換器。

【請求項4】上記論層体は電極膜を介して2層または3 層のセラミックグリーンシートを積層し、同時に焼成し て得られる焼結体よりなり、上記補層体の表裏主面に形。20・に円形の金属板を貼り付けてユニモルフ型振動板を構成 成された主面電極間に弯圧を印加することで、すべての セラミックス層を厚み方向において同一方向に分極して なることを特徴とする請求項1ないし3のいずれかに記 戴の圧弯型弯気音響変換器。

【請求項5】上記荷層体は矩形板状に形成され、上記荷 層体が、下面に開口部を有し上面に放音穴を有するケー スに収容され、上記論層体の対向する2辺が、上記ケー スの内側面対向部に形成された支持部に支持剤により支 持され、上記積層体の他の2辺と上記ケースの内側面と の間の隙間が弾性封止剤により封止され、上記ケースの 30 下面開口部が、上記論層体の主面電極と内部電極とに接 続される外部接続用電極を有する裏蓋で閉じられている ことを特徴とする請求項1ないし4のいずれかに記載の 圧電型電気音響変換器。

【請求項6】上記請層体は指形板状に形成され、上記請 歴体が、上面に開口部を有し、上記積層体の主面電極と 内部電極とに接続される外部接続用電極を有するケース に収容され、上記論層体の対向する2辺が、上記ケース の内側面対向部に形成された支持部に支持剤により固定 され、上記論層体の他の2辺と上記ケースの内面との間 40 の陰間が弾性封止剤により封止され、上記ケースの上面 関口部が、放音穴を有する上蓋で閉じられていることを 特徴とする請求項1ないし4のいずれかに記載の圧電型 **运气音鉴变换器**。

【請求項7】上記論層体は矩形板状に形成され、上記論 層体が、下面に開口部を有し上面に放音穴を有するケー スに収容され、上記論層体の4辺が、上記ケースの内側 面に形成された支持部に支持剤により固定され、上記ケ ースの下面関口部が、上記積層体の主面電極と内部電極

ていることを特徴とする語求項1ないし4のいずれかに 記載の圧弯型電気音響変換器。

【請求項8】上記積層体は矩形板状に形成され、上記積 層体が、上面に開口部を有し、上記積層体の主面電極と 内部電極とに接続される外部接続用電極を有するケース に収容され、上記補層体の4辺が、上記ケースの内側面 に形成された支持部に支持剤により固定され、上記ケー スの上面関口部が、放音穴を有する上蓋で閉じられてい ることを特徴とする請求項1ないし4のいずれかに記載 の圧電型電気音響変換器。

【発明の詳細な説明】

[0001]

【発明の属する技術分野】本発明は圧電受話器、圧電サ ウンダ、圧電スピーカ、圧電ブザーなどの圧電型電気音 響変換器、特にその振動板の構造に関するものである。 [0002]

【従来の技術】従来、圧電受話器や圧電ブザーなどに圧 常型電気音響変換器が広く用いられている。この種の圧 電型電気音響変換器は、円形の圧電セラミック板の片面 し、この振動板の国縁部を円形のケースの中に支持し、 ケースの関口部をカバーで閉鎖した構造のものが一般的 である。しかしながら、ユニモルフ型振動板の場合、電 圧印刻によって外径が伸縮するセラミック板を、寸法変 化しない金属板に接着して屈曲振動を得るものであるか ち、その変位量つまり音圧が小さいという欠点がある。 【0003】そとで、複数の圧電セラミックス層がらな る積層構造のバイモルフ型振動板が提案されている(特 開昭61-205100号公報)。この振動板は、複数 のセラミックグリーンシートおよび複数の電極を積層 し、 同時に焼成して得られた焼箱体を利用したものであ り 振動板の振動を拘束しない位置に形成されたスルー ホールにより、電極間を電気的に接続している。そし て、厚み方向に順に配置された第1および第2の振動領 域が相互に逆方向に振動するように構成することで、ユ ニモルフ型に比べて大きな変位置つまり大きな音圧を得 るととができる。

[0004]

【発明が解決しようとする課題】ところが、上記バイモ ルフ型振動板の場合、例えば3層のセラミックス層から なる振動板を屈曲振動させようとすると、上記公報の第 17回に示すように、一方の主面の電極と一方の内部電 極とをスルーホールを介して相互に接続し、他方の主面 電極と他方の内部電極とをスルーホールを介して相互に 接続した上、両者の間に交番電圧を印加する必要があ る。そのため、主面電極と内部電極との間の複雑な相互 接続が必要となり、コスト高になる可能性があった。 【りりり5】また、上記積層体に対して分極処理を行な う場合も、内部電極と衰衰の主面電極との間に電圧を印 とに接続される外部接続用電極を有する裏蓋で閉じられ 50 加して分極しなければならない。例えば3層構造の振動

(3)

板の場合、上記公報の第14図に示すように、内部電極 と導通する2個のスルーホールを接続用の電極でつな ぎ、この接続用電極と表裏の主面電極との間に高電圧を 印刷して分極している。このように、従来のバイモルフ 型振動板の場合、分極処理のために内部電極をスルーボ ールを介して外部に引き出す必要があり、接続用の電極 を形成するなど、煩雑な処理を必要とするという欠点が あった。

【①①06】そこで、本発明の目的は、主面電極と内部 フ型振動板を構成できる圧電型電気音響変換器を得るこ とにある。また、他の目的は、分極処理を簡単に行なう ことができる圧電型電気音製変換器を得ることにある。 [0007]

【課題を解決するための手段】上記目的を達成するた め、請求項1に記載の発明は、2厘または3厘の圧電セ ラミックス層を積層して積層体が形成され、この積層体 の表裏主面には主面電極が形成され、各セラミックス層 の間には内部電極が形成され、すべてのセラミックス層 面電極と内部電極との間に交替信号を印加することで、 上記積層体は全体として屈曲振動を生じることを特徴と する圧電型電気音響変換器を提供する。

【①①08】本発明の綺層体の場合。主面電極と内部電 極との間に交番電圧を印加すれば、表側および裏側のセ ラミックス層に働く電界方向が厚み方向において逆方向 になる。一方、分極方向は全てのセラミックス層が厚み 方向において同一方向に向いている。圧電セラミックス は、分極方向と電界方向とが同一方向であれば平面方向 に確む性質を有し、分極方向と電界方向とが逆方向であ 30 よく 分極処理が非常に簡単になる。 れば平面方向に伸びる性質を有している。したがって、 上記のように交番電圧を印刷すれば、表側のセラミック ス層が延びた時、裏側のセラミックス層が縮み、全体と して積層体は屈曲緩動を生じることになる。この変位置 はユニモルフ型振動板に比べて大きくなるので、音圧も

【①①①9】本発明では、表裏の主面電極を相互に接続 し、これと内部電極との間に交番電圧を印加すれば、屈 曲振動を発生させることができるので、従来のように主 面電極と内部電極との間の複雑な相互接続が不要とな り、構造が簡単になり、加工コストを低減できる。

【①①10】請求項2のように、内部電極を補層体の繼 面に形成された端面弯極と接続し、上記端面弯極と2つ の主面電極との間に交番信号を印加するのが望ましい。 この場合には、スルーホールなどの格別な加工を必要と

【1)11】請求項3のように、積層体が3層のセラミ ックス層で構成されている場合、中間のセラミックス層 の厚みを箱屋体の全体の厚みの50%~80%とするの

せばよいが、共振国波数により厚みが固定されている場 台には、綺麗敷も自由に増やすことができない。 3層標 造の積層体の場合、2つの内部電極の間には電位差がな いので、中間層は屈曲振動には寄与せず、表側および裏 側のセラミックス層のみが屈曲振動することになる。セ ラミックス層はその厚みが薄い程、変位置が大きい。そ 表裏層の厚みに対して相対的に厚くすると、屈曲振動に 寄与する表側および裏側のセラミックス層の厚みが相対 電極との相互接続をなくし、簡単な接続機造でバイモル(10)的に薄くなり、大きな変位量が得られる。なお、中間層 の厚みを大きくし過ぎると、表裏層の厚みが薄くなり過 ぎ、強度が低下して大きな変位が得られない。そこで、 中間層の厚みを全体の50%~80%の範囲とすること で、大きな音圧を得ることができる。

【0012】請求項4のように、綺層体は電極膜を介し て2層または3層のセラミックグリーンシートを積層 し、同時に焼成して得られる焼結体よりなり、積層体の 表裏主面に形成された主面電極間に電圧を印加すること で すべてのセラミックス層を厚み方向において同一方 は厚み方向において同一方向に分極されており、上記主 20 向に分極するのが望ましい。すなわち、予め焼成し分極 処理したセラミック板を複数技績層接着して積層体を得 ることも可能であるが、これでは讀層体の厚みを薄くで きず、音圧が小さい。これに対し、セラミックグリーン シートを電極膜を間にして積層し、同時焼成すれば、非 意に薄い積層体を得ることができ、高い音圧を得ること ができる。しかも、請屈体の各セラミックス層の分極方 向が同一方向を向いているので、その分極処理は、従来 のように内部電極と主面電極との間に電圧を印加する必 要がなく、表裏の主面電極の間に電圧を印加するだけで

> 【0013】上記論層体をハウジング内に収容し、圧電 受話器や圧電サウンダのような発音体として用いる場 台、請求項5~8に記載のような構造とすることができ る。すなわち、請求項5、6は受話器としての用途に適 した例であり、広いレンジの国波数に対応するため、共 振領域以外の領域で使用される。そのため、積層体の振 動エネルギーが比較的小さいので、積層体の対向する2 辺だけをケースに支持し、他の2辺は弾性對止体で変位 自在に封止した構造となっている。一方、請求項で、8 46 は圧電サウンダなどの用途に適した例であり、単一周波 数での大音量に対応するため、共振領域で使用される。 この場合には、積層体の振動エネルギーが非常に大きい ので、綺層体の4辺すべてをケースに支持した構造とな っている。いずれの構造も、補層体の主面電極と内部電 極とをリード線を使用せずにハウシングの外部に引き出 すことができるので、表面実装部品として構成すること ができる。

[0014]

【発明の実施の形態】図1、図2は本発明にかかる圧電 が望ましい。音圧を高めるには、満層体の満層数を増や 50 型電気音響変換器の第1実超例を示す。この圧電型電気 音響変換器は、円板状の振動板(積層体)1と、この振 動板1を収容した円形のケース10および裏蓋11とで 構成されている。ケース10の上面には放音穴12が形 成され、下面開口部に哀蓋11が接着されている。ケー ス10の外国部の対称位置には、外部接続用端子13, 14がインサート成形などにて固定され、蝎子13,1 4の一部はケース10の内側に舞出している。端子1 3. 14の内側窓出部に、振動板1の電極が導電性接着 剤15、16によって電気的に接続されている。なお、 の外層部とケース10との隙間は、シリコーンゴムなど の弾性封止剤(図示せず)で封止されている。

【0015】振動板1は、図3、図4に示すようにP2 丁などからなる2層の圧電セラミックス層2、3を綺層 したものであり、振動板1の表裏主面には主面電極4, 5が形成され、セラミックス層2、3の間には内部電極 6が形成されている。2つのセラミックス層2、3は、 図4に太淑矢印で示すように厚み方向において同一方向 に分極されている。

の主面電極5は、振動板1の直径よりやや小さい円形に 形成され、その引出電極4 a, 5 a が振動板1の外国線 まで引き出されている。内部電極6は主面電極4、5と ほぼ対称形状に形成され、内部弯極6の引出弯便6 a は 上記引出電極4 a, 5 a とほぼ対称位置へ引き出され、 **端面に設けられた端面電極?に接続されている。なお、 端面電極7の一部は振動板1の表裏面まで引き出されて** いる。上記引出電極4 a、5 a は導電性接着削15によ って端子13と接続され、端面電極では導電性接着剤1 6によって端子14と接続されている。そして、端子1 3、14の間に所定の交番電圧を印加することで、緩動 板1を屈曲振動させることができる。

【0017】例えば一方の端子13にマイナスの電圧、 他方の鑷子14にプラスの電圧を印削すると、図4の細 線矢印で示す方向の電界が生じる。 セラミックス層2, 3は、分極方向と電界方向とが同一方向であれば平面方 向に縮む性質を有し、分極方向と電界方向とが逆方向で あれば平面方向に伸びる性質を有するので、表側のセラ ミックス層2は縮み、裏側のセラミックス層3は伸びる ことになる。そのため、振動板1は中心部が下方へ凸と 40 なるように屈曲する。端子13,14に印加する電圧を 交番電圧とすれば、振動板1は周期的に屈曲振動を生 じ、これによって大きな音圧の音を発生することができ る.

【0018】上記機成よりなる振動版1は次のような方 法で製造される。 すなわち、マザー基板状態のセラミッ クグリーンシートの表面に電極膜を印刷などの手法で所 定のバターンに形成し、このセラミックグリーンシート 1枚と、電極膜を形成していないセラミックグリーンシ ート1枚とを積層して圧着する。次に、この積層体から 50 が完成する。

振動板」に対応する形状に打ち抜き、あるいはカットす る。次に、打ち抜きまたはカットされた論層体を同時焼 成して焼結積層体を得る。次に、焼結積層体の表裏主面 に主面電極を形成し、これら主面電極間に分極電圧を印 加することで、積層体を構成する全てのセラミックス層 を厚み方向において同一方向に分極する。その後、 端面 電便?などを形成し、振動板!を得る。

【0019】上記製造方法では、積層されたマザー基板 状態のセラミックグリーンシートを個別形状に打ち抜い 導電性接着剤15,16を塗布した箇所以外の振動板1 10 た後、焼成し、その後で分極処理したが、積層されたセ ラミックグリーンシートを焼成した後、マザー蟇板状態 で分極処理し、その後で個別形状にカットしてもよい。 この場合には、原結体をカットするために、レーザー加 工などの公知の方法を用いればよい。

【①①20】図5、図6は本発明にかかる圧電型電気音 響変換器の第2実施例を示す。図1、図2では、ケース 10に固定された選子13、14を用いて振動板1の電 極を外部へ引き出したが、図5、図6ではリード線2 21を用いたものである。この場合には、リード線 【①①16】との裏施例では、表側の主面電極4と裏側 20 20、21が振動板1の裏面側の主面電極5と端面電極 7とにそれぞれ半田や導電性接着剤などの接合剤22, 23によって接続される。そのため、表裏の主面電極 4. 5を導電性接着剤を用いて相互に接続してもよい し、予め端面電極によって主面電極4、5を接続してお いてもよい。

> 【①①21】図7、図8は本発明にかかる圧電型電気音 響変換器の第3 実施例を示す。この圧電型電気音響変換 器は、長方形の振動板(積層体)30と、この振動板3 ①を収容した角形のケース40および裏蓋41とで構成 されている。ケース40の上面には放音穴42が形成さ れ、下面関口部に裏蓋41が接着されている。ケース4 ①の対向する2辺の内側面には段差状の支持部42a, 42 bが形成され、これら支持部42 a, 42 b上に振 動板30の短辺側の2辺が接着剤などの支持剤43a, 43 bによって支持されている。ケース40の支持部4 2a、42hを設けた側面とは異なる側面には、制動孔 48が形成されている。また、振動板30の長辺側の2 辺とケース40との隙間はシリコーンゴムなどの弾性封 止削448、44りによって封止されている。裏蓋41 の両端部表裏面には外部接続用電極45a, 45bが形 成されており、表裏の弯便45a,45bは裏蓋41の 両端部側縁に形成されたスルーホール潜468.46b の内面を介して相互に導通している。

【0022】裏蓋41をケース40の下面関口部に接着 した後、図8に示すようにスルーホール操46a、46 りから導電性接着剤47a、47bを流し込むことで、 外部接続用電極45a, 45bと振動板30の電極とが 相互に接続されるとともに、スルーホール漢46a,4 6 bが閉じられる。これにより、圧電型電気音響変換器

【0023】との実施例の振動板30は、図9、図10 に示すように、2厘の圧電セラミックス層31、32を **箱磨したものであり、振動板30の表裏主面には主面弯** 極33、34が形成され、セラミックス層31、32の 間には内部電極35が形成されている。2つのセラミッ クス層31、32は、図10に太線矢印で示すように厚 み方向において同一方向に分極されている。

【10024】この裏施例では、表側の主面電極33と裏 側の主面電極34は、振動板30の短辺と同幅でかつ長 辺よりやや短く形成され、その一端は振動板30の一方。10 に厚み方向において同一方向に分極されている。 の短辺側端面に形成された端面弯極36に接続されてい る。そのため、表裏の主面電極33、34は相互に接続 されている。内部電極35は主面電極33,34とほぼ 対称形状に形成され、内部電極35の一端は上記端面電 極36と離れており、他端は振動板30の他方の短辺側 端面に形成された端面電極37に接続されている。な お、振動板30の他方の短辺側總部の上下面には、總面 電極37と導通する細幅な補助電極38が形成されてい る.

4は、図8のように導弯性接着剤47aによって外部接 続用電極45aと接続され、端面電便37は導電性接着 剤47 bによって外部接続用電極45 bと接続されてい る。そして、外部接続用電極45a、45bの間に所定 の交番電圧を印刷することで、振動版30を長さベンデ ィングモードで屈曲振動させることができる。すなわ ち、振動板30の短辺側両端部を支点とし、長手方向の 中央部を最大振帽点として屈曲録動させることができ

【① 026】第1実施例のような円形振動板1の場合に は、中心部のみが最大振幅点となるため、変位体積が小 さく、音響変換効率が比較的低い。また、振動板1の周 圏が拘束されるので、風波敷が高くなり、低い周波数の 圧電振動板を得ようとすれば、半径寸法が大きくなる。 これに対し、第3実施例のような矩形振動板30の場合 には、最大振幅点が長さ方向の中心線にそって存在する ので、変位体積が大きく、高い音響変換効率を得ること ができる。また、振動板30はその長さ方向両端部が固 定されるが、その間の部分は弾性封止剤44a、44b によって自由に変位できるので、円形の振動板に比べて 低い周波数を得ることができる。逆に、同じ周波数を得 るのであれば、寸法を小型化できる。

【0027】図11は、図10の変形例である。振動板 の第4実施例を示す。図10では内部電極35が部分電 極である例を示したが、図11では全面電極としたもの である。この場合には、内部電極35が端面電極36側 まで延びているので、内部電極35と端面電極36とが 導通してしまう恐れがある。そこで、振動板30°の端 面にまず絶縁層39を形成し、その上に表裏の主面等極

ある。これにより、内部電便35を全面電極とした場合 でも、内部電極35と主面電極33、34とを確実に絶 緑できる。

【10028】図12は振動板の第5実能例を示す。この 実施側の振動板50は、3層の圧電セラミックス層51 ~53を補煙したものであり、振動板50の豪裏面には 主面電極54、55が形成され、各セラミックス層51 ~53の間には内部電極56,57が形成されている。 3つのセラミックス層51~53は太線矢印で示すよう

【0029】との実施例の主面電極54,55は、図1 0 と同様に振動板50の短辺と同幅でかつ長辺よりやや 短く形成され、その一端は振動板50の一方の短辺側端 面に形成された端面電極58に接続されている。そのた め、表裏の主面電極54、55は相互に接続されてい る。内部電極56,57の一端は鑑面電極58と離れて おり、他繼は振動板50の他方の短辺側繼面に形成され た端面穹極59に接続されている。したがって、内部穹 極56、57も钼互に接続されている。なお、振動板5 【0025】上記總面電極36または裏側の主面電極3 20 0の他方の短辺側端部の上下面には、端面電極59と導 通する細幅な補助電極59aが形成されている。

> 【0030】例えば、蝶面電極58にマイナスの電圧、 場面電極59にプラスの電圧を印加すると、図12の細 線矢印で示す方向の電界が生じる。この時、中間層であ るセラミックス層52の両側に位置する内部電極56, 57は同一電位であるため、電界が生じない。表側のセ ラミックス層51は分極方向と電界方向とが同一方向で あるため平面方向に縮み、裏側のセラミックス層52は 分極方向と無界方向とが逆方向であるため平面方向に伸 びる。そして、中間層52は伸び縮みしない。そのた め、振動板50は下方へ凸となるように屈曲する。 端面 電極58,59間に交響電圧を印加すれば、振動板50 は周期的に屈曲振動を生じ、これによって大きな音圧の 音を発生することができる。なお、図12では、内部電 極56,57を部分電極としたが、図11のように全面 電極としてもよい。

【①①31】上記のような3層構造の振動板50の製造 方法も、図4に示した2層構造の振動板1の製造方法と 同様である。すなわち、マザー基板状態のセラミックグ リーンシートの表面に電極機を印刷などの手法で所定の パターンに形成し、このセラミックグリーンシートを3 枚積層して圧着する。この積層体から振動板50に対応 する形状に打ち抜きまたはカットし、この打ち抜きまた はカットされた積層体を同時焼成して焼結積層体を得 る。次に、焼結積層体の表裏面に主面電極54、55を 形成し、これら主面電極間に分極電圧を印加すること で、積層体を構成する全てのセラミックス層51~53 を厚み方向において同一方向に分極する。その後、 端面 電極58、59などを形成することで、振動板50を得 33、34を導通させる端面障極36を形成したもので 50 る。この場合も、分極に際し、内部電極56,57と主

の主面電極54、55間に電圧を印加するだけでよいの で、分極処理が簡単である。

【()()32]図13は振動板の第6実施例を示す。図1 2の実施例では3厘のセラミックス層51~53がほぼ 同一厚みである例を示したが、図13では中間のセラミ ックス層52を表裏のセラミックス層51,53に比べ て厚くしたものである。特に、中間のセラミックス層5 2の厚みは、振動板50°の全体の厚みの50%~80 であるため、重複説明を省略する。

【() () 3 3 】図 1 4 は中間セラミックス層 5 2 の厚みの 割合を変化させた時の音圧の変化を示す。縦軸は2層機 造の振動板(図10参照)の音圧を1とした時の音圧の 比率であり、横軸は振動板50.の全体の厚みに対する 中間セラミックス層52の厚みの割合を表す。なお、音 圧は、振動板50 の全体の厚みが一定で、かつ印加湾 圧が一定である条件で測定した。

【()()34]図14から明らかなように、2層に比べて 層すべてが同一厚みである場合(33%)に比べて、中 間層の厚みを全体の50%~80%とした場合には、さ ちに音圧が上昇する。特に、中間層の厚みを全体の60 %~?()%とした場合に最大の音圧(2層に比べて). 6倍)を得ることができる。したがって、補層数に制約 がある場合に、中間層の厚みを大きくすることで、積層 数を少なく(3層)しながら、音圧を最大限まで上げる ことができる。

【0035】図15~図17は本発明にかかる圧電型電 気音響変換器の第7実施例であり、表面実装型の圧電受 30 話器として構成した例を示す。この圧電受話器は、大 略、長方形の振動板(積層体)30と、この振動板30 を収容した角形のケース60と、放音孔69を有する上 **蓋68とで構成されている。振動板30は図9、図10** に示されたものと同様であるため、同一符号を付してあ る。ケース6()は、例えばLCP(液晶ポリマー), S PS(シンジオタクチックポリスチレン), PPS(ボ リフェニレンサルファイド)、エポキシなどの耐熱性樹 脂で形成され、上蓋68も液晶ポリマーまたはガラスエ ボキシなどの耐熱性材料あるいはセラミックスで形成さ 40 30 , 50、50 を用いることも可能である。 れている。ケース60の上面には関口部61が形成さ れ、この上面開口部61に上蓋68が接着されている。 ケース60の対向する2辺の内側面には段差状の支持部 62a, 62bが形成され、これら支持部62a、62 りの上面とケース60の外側面とに露出するように、外 部接続用電極63a,63bがインサート成形されてい る。この外部接続用電極63a,63bとしては、例え ばAu、Snメッキを施したCu合金、Feなどからな る金属端子で構成される。ケース60の支持部628. 62bを設けた側面とは異なる側面には、制動孔64が 50 の発音器として用いられるものであり、振動板30の全

形成されている。

【0036】振動板30の短辺側の2辺は、支持部62 a. 62 h上に接着削などの支持削65 a. 65 bによ って支持されている。また、振動板30の長辺側の2辺 とケース60との隙間はシリコーンゴムなどの弾性封止 剤66a,66bによって封止されている。そして、娠 動板30の短辺側の2辺に設けられた端面弯極36,3 7は、 夢電ペースト67a、67bによって支持部62 a. 62 bの上面に露出した外部接続用電極63 a, 6 %とするのが望ましい。なお、他の構造は図12と同様 10 3 p とそれぞれ電気的に接続されている。なお、支持剤 65a, 65bおよび弾性封止剤66a, 66bの塗布 は、遵電ペースト67a、67ヵによって振動板30と 外部接続用電弧63a,63bとを接着した後で行う方 がよい。そして、導電ペースト67a、67b、支持剤 65a, 65bおよび弾性封止剤66a, 66bの加熱 硬化は、同時に行ってもよい。

【①①37】図18は本発明にかかる圧電型電気音響変 換器の第8実施例であり、図15~図17に示された例 の変形例である。この真能例では、外部接続用電極63 3層の場合には音圧が上昇することが分かる。また、3~20~a、63hが、ケース60にインサートされたものでは なく、別体に形成された金属端子をケース60の孔60 aに挿入し、接着したものである。その他の構造は図1 5~図17と同様であるから、同一部品には同一符号を 付して説明を省略する。

> 【①①38】図19~図21は本発明にかかる圧電型電 気音響変換器の第9実施例であり、表面突接型部品とし て構成した例を示す。この実施例では、図15~図17 におけるインサート幾子よりなる外部接続用電極63 a、63bに代えて、無電解湿式めっき法あるいはスパ ッタなどの乾式めっき法により形成した電極膜63c. 63aとしたものである。この例では、電極膜63c, 63 dがケース60の支持部62 a. 62 bを設けた側 部の外面から支持部62a.62bの上面にかけて連続 的に形成されている。その他の構成は図15~図17の ものと同様であるから、同一部品には同一符号を付して 説明を省略する。

> 【()()39】なお、図15~図21に示す裏施側におい て、振動板としては、図9、図10に示された振動板3 ()に限らず、図11,図12,図13に示された振動板

> 【① ① 4 ① 】図2 2 は本発明にかかる圧電型電気音響変 換器の第10実施例である。この実施例は、図7に示す 実施例の変形例であり、図7と同一部分には同一符号を 付して説明を省略する。図22は裏側から見た斜視図で あり、ケース4() の内側面全層に段差状の支持部42 が形成されている。これら支持部42の頂面は同一高さ に形成されており、支持部42上に振動板30の4辺全 園が接着剤などの支持剤43によって支持されている。 この実施例は、例えば圧電サウンダなどの単一周波数で

(2)

園が支持剤43によって拘束されるが、緩動板30を共 振領域で使用することにより、強く励振させることがで き、大音量を得ることができる。

11

【①①41】図23は本発明にかかる圧電型電気音響変 換器の第11実施例である。この実施例は、図15~図 1.7に示す実施例とほぼ同様な構造を有し、図15~図 17と共通部分には同一符号を付して説明を省略する。 この実施例では、角形のケース60の内側面全層に段差 状の支持部62が形成され、振動板30の4辺すべてが 支持部62に対して接着削などの支持剤65によって支 10 板の斜視図である。 持されている。この実施例も、圧電サウンダなどの単一 国波数での発音器として用いられる例であり、振動板3 ()は共振領域で使用される。

【①①42】本発明は上記実施例に限定されるものでは なく、本発明の趣旨を逃脱しない範囲で種々変更が可能 である。上記実施例では、振動板の端面に内部電極と導 通する端面電極を形成し、この端面電極を介して外部へ 引き出すようにしたが、これに限るものではない。すな わち、特開昭61-205100号公報のようにスルー ホールを介して内部電極を外部へ引き出してもよいし、 20 板の斜視図である。 スリット状の潜あるいは穴を介して外部へ引き出しても よい。上記突結例の振動板 1, 30, 30, 50, 5 の製造方法は、セラミックグリーンシートを電極膜 を介して2枚または3枚積層し、この積層体を同時焼成 して統結論層体を得た後、この焼結積層体を分極処理す るものであるが、この方法に代えて、予め焼成し分極処 **廻した2枚または3枚の圧電セラミックス板を積層接着** してもよい。ただし、積層後に焼成する前者の製造方法 は、予め焼成したものを積層する後者の方法に比べて、 振動板の厚みを格段に薄くでき、音圧を大きくできるの 30 で、前者の製造方法の方が音響変換効率に優れた振動板 を得ることが可能である。本発明の振動板は、圧電セラ ミックス層のみで構成されたものに限らず、積層体の片 面に金属フィルムや樹脂シートなどの構強シートを貼り 付けてもよい。但し、この補強シートはユニモルフ型振 動板の金属板とは異なり、積層体の割れなどを防止する ためのものであり、補層体の層曲振動を阻害しないもの が望ましい。

#### [0043]

【発明の効果】以上の説明で明らかなように、請求項1 40 に記載の発明によれば、2層または3層の圧電セラミッ クス層からなる積層体の表裏面に主面電極を形成し、各 セラミックス層の間に内部電極を形成し、すべてのセラ ミックス層を厚み方向において同一方向に分極したの で、主面電極と内部電極との間に交番信号を印加すれ は、表側と裏側のセラミックス層が逆方向に伸縮し、全 体として積層体が屈曲振動を生じることになる。この変 位量はユニモルフ型振動板に比べて大きくなるので、音 圧も増大する。また、すべてのセラミックス層が厚み方

な主面電極と内部電極との間の複雑な相互接続が不要で あり、主面電極と内部電極との間に交番信号を印加する だけでよく、構造が簡単で、製造コストを低減できる。

【図面の簡単な説明】

【図1】本発明にかかる圧電型電気音響変換器の第1実 施例の外観斜視図である。

【図2】図1に示す圧弯型電気音響変換器の縦断面図で

【図3】図1の圧電型電気音響変換器に用いられる振動

【図4】図3に示す振動板の縦断面図である。

【図5】本発明にかかる圧電型電気音響変換器の第2実 施例の外観斜視図である。

【図6】図5に示す圧電型電気音響変換器の縦断面図で ある。

【図7】本発明にかかる圧電型電気音響変換器の第3 実 施例を裏側から見た分解斜視図である。

【図8】図7の圧電型電気音響変換器の断面図である。

【図9】図7の圧弯型電気音響変換器に用いられる振動

【図10】図9の振動板の断面図である。

【図11】本発明にかかる振動板の第4実施例の断面図 である。

【図12】本発明にかかる振動板の第5実施例の断面図 である。

【図13】本発明にかかる振動板の第6実施例の断面図

【図14】図13に示す振動板を用いた圧電型電気音響 変換器の中間層の厚みと音圧との関係を示す特性図であ

【図15】本発明にかかる圧電型電気音響変換器の第7 実施側の斜視図である。

【図16】図15に示す圧電型電気音響変換器の分解料 視図である。

【図17】図15のA-A線断面図である。

【図18】本発明にかかる圧電型電気音響変換器の第8 **真縫側の分解斜視図である。** 

【図19】本発明にかかる圧電型電気音響変換器の第9 真緒側の斜視図である。

【図20】図19に示す圧電型電気音響変換器の分解料 復図である。

【図21】図19のB-B線断面図である。

【図22】本発明にかかる圧電型電気音響変換器の第1 ()実施例の分解斜視図である。

【図23】本発明にかかる圧電型電気音響変換器の第1 1 実能例の分解斜視図である。


【符号の説明】


1, 30, 30', 50, 50' 振勤板

2、3,31、32,51~53 セラミックス層

向において同一方向に分極されているので、従来のよう「50~4.5,33.34,54.55」主面電極

1/11/2006





特闘2001-95094

#### 【手続補正書】

【提出日】平成12年7月18日 (2000.7.1 8)

【手統結正 1 】

【補正対象書類名】明細書

【補正対象項目名】0013

【補正方法】変更

#### 【補正内容】

【0013】上記綺層体をハウジング内に収容し、圧電 受話器や圧電サウンダのような発音体として用いる場 台、請求項5~8に記載のような構造とすることができ る。すなわち、請求項5、6は受話器としての用途に適 した例であり、広いレンジの国波数に対応するため、共米

\*振領域以外の領域も使用される。そのため、積層体の振 動エネルギーが比較的小さくても変位できるように、積 層体の対向する2辺だけをケースに支持し、他の2辺は 弾性封止体で変位自在に封止した構造となっている。一 方、請求項7、8は圧電サウンダなどの用途に適した例 であり、単一周波数での大音量に対応するため、共振領 域で使用される。この場合には、積層体の振動エネルギ ーを大きくするため、領層体の4辺すべてをケースに支 持した構造となっている。いずれの構造も、結層体の主 面電極と内部電極とをリード線を使用せずにハウジング の外部に引き出すことができるので、表面突続部品とし て構成することができる。

フロントページの続き

#### (72) 発明者 山本 隆

京都府長岡京市天神2丁目26香10号 株式 会社村田製作所内

#### (72) 発明者 濱田 和朗

(10)

京都府長岡京市天神2丁目26香10号 株式 会社村田製作所内

# This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

### **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

□ BLACK BORDERS
□ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
□ FADED TEXT OR DRAWING
□ BLURRED OR ILLEGIBLE TEXT OR DRAWING
□ SKEWED/SLANTED IMAGES
□ COLOR OR BLACK AND WHITE PHOTOGRAPHS
□ GRAY SCALE DOCUMENTS
□ LINES OR MARKS ON ORIGINAL DOCUMENT
□ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

### IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

□ OTHER: